

Amendments to the Claims

1. (Currently amended) A large surface area electrode comprising

a substrate member having current collecting ability and

metallic fiber tow comprising a multiplicity of fine metallic fibers having a surface,

wherein said metallic fiber tow is disposed upon said substrate member in a wound manner,

whereby said large surface area electrode has large active surface area and is easy to manufacture.

2. (Withdrawn) The large surface area electrode of claim 1, wherein said metallic fiber is a metallic fiber tow comprising a multiplicity of fine metallic fibers.

3. (Currently amended) The large surface area electrode of claim 1 [[2]], wherein said substrate member is essentially a flat piece of sheet metal.

4. (Original) The large surface area electrode of claim 3, wherein at least part of said surface of said metallic fiber tow is covered with an electrocatalytic coating having an outermost surface composition.

5. (Original) The large surface area electrode of claim 4, wherein said metallic fiber tow has a composition selected from the class consisting of titanium and titanium alloys.

6. (Original) The large surface area electrode of claim 5, wherein said outermost surface composition comprises titanium dioxide doped with one or more additive metals selected from

the group consisting of niobium in the +4 valence state, tantalum in the +4 valence state, and antimony,

whereby an electrode useful for water purification is produced.

7. (Original) The large surface area electrode of claim 5, wherein said electrocatalytic coating contains at least one platinum group metal.

8. (Withdrawn) The large surface area electrode of claim 1, wherein said metallic fiber comprises one or more fine wires having a surface and having a composition chosen from the class consisting of titanium and titanium alloys, and at least part of said surface of said fine wires is coated with an electrocatalytic coating containing at least one platinum group metal.

9. (Currently amended) The large surface area electrode of claim 1 ~~[[2]]~~, wherein said metallic fiber tow is crimped.

whereby an advantageously fluffy electrode structure is provided.

10. (Currently amended) The large surface area electrode of claim 1 ~~[[2]]~~, further provided with means for improving electrical contact of said metallic fiber tow with said substrate member ~~[[enhancement means]]~~.

11. (Currently amended) The large surface area electrode of claim 10, wherein said large surface area electrode has edges, and said means for improving electrical contact ~~[[enhancement means]]~~ comprise edge strips applied to said edges.

12. (Currently amended) The large surface area electrode of claim 10, wherein said means for improving electrical contact ~~[[enhancement means]]~~ comprise nonconductive spacers disposed adjacently to said large surface area electrode.

13. (Currently amended) The large surface area electrode of claim **1** ~~[[2]]~~, further provided with means for improving electrical isolation ~~[[means]]~~ between said large surface area electrode and an adjacently disposed counterelectrode.

14. (Currently amended) The large surface area electrode of claim **13**, wherein said means for improving electrical isolation ~~[[means]]~~ comprise at least one layer of a nonconductive mesh having a composition and disposed adjacently to said large surface area electrode.

15. (Original) The large surface area electrode of claim **14**, wherein said composition of said nonconductive mesh is chosen from the class consisting of polypropylene, polyethylene and vinyl coated fiberglass.

16. (Original) The large surface area electrode of claim **3**, wherein said metallic fiber tow comprises essentially a single layer of said metallic fiber tow covering at least a part of said substrate member.

17. (Original) A method to produce a large surface area electrode, comprising the step of winding multiple turns of a metallic fiber tow on to a metallic substrate member having a substantially planar geometry.

18. (Original) The method of claim **17**, with the precursor step of mechanically crimping said metallic fiber tow prior to winding it on to said metallic substrate member.


19. (Original) The method of claim **17**, with the subsequent step of applying an electrocatalytic coating to said large surface area electrode.

20. (Original) The method of claim **17**, with the precursor step of applying an electrocatalytic coating to said metallic fiber tow.

Authorization for Payment of Fees

In the event that this Amendment requires that additional fees be paid, Common Representative for Applicants Pro Se Oleh Weres hereby authorizes the US-PTO to charge his credit card identified in the Credit Card Payment Authorization form attached hereto.

Very respectfully,



Oleh Weres, Common Representative for Applicants Pro Se
US-PTO Reg. No. 57,499

Correspondence address:

Oleh Weres
c/o Sonoma Research Company
101 S. Coombs Street, Suite L
Napa, CA 94559

Tel. (707)252-4620; Fax (707)252-8362

Certificate of Mailing: I certify that on the date below this document and referenced attachments, if any, will be deposited with the U.S. Postal Service as first class mail in an envelope addressed to:

Mail Stop Amendment
Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

2006 January 17



Oleh Weres, Common Representative for Applicants Pro Se
US-PTO Reg. No. 57,499